



Nitrile Powder Free CF*

Product Description

POWDER FREE NITRILE EXAMINATION GLOVE, COMFORT FORMULATION (CF),
NATURAL RUBBER **LATEX FREE**, AMBIDEXTROUS, MICRO-TEXTURED

Product Reorder Numbers

Size	Reorder Number
Small	212-21
Medium	212-22
Large	212-23
X-Large	212-24

Standards of Conformance

Standard	Description
ASTM D-6319	Standard Specification for Nitrile Examination Gloves
ASTM D-5151	Standard Test Method for the Detection of Holes in Medical Gloves
ASTM D-6184	Standard Test Method for Residual Powder on Medical Gloves
ASTM F-1671-97	Standard Test for Viral Penetration
EN 455-1	Medical Gloves for Single Use Requirements & Testing for Freedom of Holes
EN 455-2	Medical Gloves for Single Use Requirements & Testing for Physical Properties
MIL-STD-105E (ISO 2859)	Sampling Procedures and Tables

Technical Information

MATERIAL	Carboxylated Butadiene acrylonitrile and compounding materials safe for use in medical gloves. Does not contain Carbamates, Thiurams and Mercaptobenzothiozole (MBT). These gloves have been tested for use with Chemo Therapy drugs. Specific chemical data resistance available upon request. Review MSDS for specific Chemo Therapy chemicals being used to determine the best level of protection.
GLOVE DESIGN	Ambidextrous, textured with beaded cuff. 9.5 inch length.
PACKAGING	100 gloves per box, 10 boxes per case. Dispenser Box Dimensions (mm): 246 (L) x 119(W) x 83(H) Approximate weight: 1.9 lbs Outer Carton Dimensions (mm): 430(L) x 247(W) x 256(H) Approximate weight: 19 lbs
Minimum Thickness (Single Thickness)	Finger Tip 0.10mm (~4.0 mil) Palm 0.07mm (~2.8 mil) Cuff 0.06mm (~2.4 mil)
Minimum Length	Small 240 mm Medium 240 mm Large 240 mm X-Large 240 mm
Minimum Width at Palm	Small 85mm ± 5 Medium 95mm ± 5 Large 106mm ± 5 X-Large 116mm ± 5
Tensile Strength	<u>Unaged</u> 14 (MPa) <u>Aged</u> 14 (MPa)
Elongation	<u>Unaged</u> 500% <u>Aged</u> 400%
Residual Protein Content ASTM D3578 & D5712 Standard	Contains No Natural Rubber Latex
Powder Content	Powder Free, <2mg total powder per glove
AQL for Pinholes ASTM D5151 Standard	2.5



360 Route 101, Bldg 3, Bedford, NH 03110
Tel: 888-999-6664 info@omnigloves.com