



Vinyl Powder Free

Product Description

POWDER FREE VINYL EXAMINATION GLOVE
NON-LATEX, AMBIDEXTROUS
DOP (di-octyl phthalate) / DEHP (di-2-ethylhexyl phthalate) FREE

Product Reorder Numbers

Size	Reorder Number
Small	312-11
Medium	312-12
Large	312-13
X-Large	312-14

Standards of Conformance

Standard	Description
ASTM D-5250-92	Standard Specification for Polyvinyl Chloride Examination Gloves
ASTM D-5151	Standard Test Method for the Detection of Holes in Medical Gloves
ASTM D-6124	Standard Test Method for Residual Powder on Medical Gloves
ASTM D-5712	Standard Test Method for Analysis of Protein in Natural Rubber and its Products
EN 455-1	Medical Gloves for Single Use Requirements & Testing for Freedom of Holes
EN 455-2	Medical Gloves for Single Use Requirements & Testing for Physical Properties
MIL-STD-105E (ISO 2859)	Sampling Procedures and Tables

Technical Information

MATERIAL	Polyvinyl Chloride and compounding materials safe for use in medical gloves	
GLOVE DESIGN	Ambidextrous, with beaded cuff. 9.5 inch length.	
PACKAGING	<p>100 gloves per box, 10 boxes per case.</p> <p>Dispenser Box Dimensions (mm): 237(L), 117(W), 73(H) Approximate weight: 2.1 lbs</p> <p>Outer Carton Dimensions (mm): 380(L), 244(W), 250(H) Approximate weight: 21 lbs</p>	
Minimum Thickness(Single Thickness)	Finger Tip	0.09mm +/- 0.03 (~3.6mil)
	Palm	0.11mm +/- 0.03 (~4.4 mil)
	Cuff	0.08mm +/- 0.03 (~3.2 mil)
Minimum Length	Small	240 mm
	Medium	240 mm
	Large	240 mm
	X-Large	240 mm
Minimum Width at Palm	Small	85mm ± 5
	Medium	95mm ± 5
	Large	105mm ± 5
	X-Large	115mm ± 5
Tensile Strength	<u>Unaged</u> 11 (MPa)	<u>Aged</u> 11 (MPa)
Elongation	<u>Unaged</u> 300%	<u>Aged</u> 300%
Residual Protein Content ASTM D3578 & D5712 Standard	Contains No Natural Rubber Latex	
Powder Content	Powder Free, <2mg total powder per glove	
AQL for Pinholes ASTM D5151 Standard	2.5	



360 Route 101, Bldg 3, Bedford, NH 03110
Tel: 888-999-6664 info@omnigloves.com